

ULTIMATE PLUS-25
HIGH GLOSS FLOOR FINISH
PERFORMANCE LINE

DESCRIPTION

Scot's TUFF™ *Ultimate PLUS-25 High Gloss Floor Finish *Performance Line** is a premium high-quality, high solids, metal interlock floor finish. *Ultimate PLUS-25* withstands heavy traffic with the highest durability and gloss available in the industry. This product requires little maintenance. Surface dirt can be easily removed and the brilliant gloss restored by damp mopping with Scot's TUFF *All-Purpose Neutral Cleaner*. Light scratches and heel marks can be removed by using Scot's TUFF *Mop & Buff Gloss Restorer* or Scot's TUFF *Mirage Spray Buff*, then buffing with a low- to medium-speed buffing machine using a nylon polishing pad.

APPLICATIONS AND USES

Recommended for use on all types of resilient floors including vinyl, asphalt, vinyl asbestos, cork, linoleum, terrazzo, quarry tile, and marble floors. Use in high traffic areas such as hallways, entrance and exit ways, kitchens, and anywhere a high gloss is desired. *Ultimate PLUS-25* is not recommended for use on wood floors.

DIRECTIONS FOR USE

Floor Preparation: Begin by stripping with Scot's TUFF *Super Stripper No-Rinse Stripper* or *Stripper II Non-Ammoniated Stripper* to remove all dirt, wax and finish, restoring floor to its natural condition. Be sure floor has old finish completely removed and no puddles of stripper remain along aisles or corners. Be sure floor is completely dry before applying floor finish. Application: Use new or clean mops or lamb's wool applicators, which have only been used for finishes. Work on small areas at a time to prevent finish from drying before the small area has been completely coated with finish. Wring finish from mop so there is enough finish to prevent mop from dragging on floor but not so much as to cause puddling. Outline the perimeter of the small area with the mop. Coat the center of the area by applying finish in an overlapping figure 8 motion with mop. Do not rub in finish or go over the area again before it is dry. Allow finish to dry completely before applying additional coats. Normal drying time is about 30 minutes but may vary with temperature and humidity. Reapply additional coats until the desired gloss is achieved. Normally 3-4 coats are sufficient. The gloss will increase each time the floor is buffed. NOTE: Never pour partially used finish back into the original container; it will contaminate the remaining product.

FEATURES AND BENEFITS

- Resists scuffing and heel marks
- Durable "wet look" finish
- Requires little maintenance
- APE and formaldehyde free

TECHNICAL DATA

Appearance..... White, milky liquid
 pH..... 9.2
 Slip Resistance... >0.5 (James Machine)
 Stability..... Freeze/thaw stable

ITEM #	PACKAGED	DILUTION RATIO	COVERAGE RATE
0A4211	1 Gallon Round 4/case	Ready-to-use	1500 - 2000 sq. ft./gallon
0A4212	5 Gallon Pail each		(depending on porosity of
0A4213	55 Gallon Drum each		floor)